



TECHNICAL DATA SHEET

PURONOL—606

NATURAL & SYNTHETIC PHOSPHATED FATTY POLYMER

Appearance	: Light Brown Viscous Liquid
Character	: Anionic
pH of 10% solution	: 6.5 to 7.5
Active matter (%w/w)	: 38% ± 2
Emulsion Stability	: Excellent Emulsify at low Temperature.
Light Fastness	: Excellent: can be used for white & Light fast articles.
Product Compatibility	: Compatible with regular synthetic and natural Sulphited Oils and marine fatliquor.
Product Benefits	: PURONOL 606 does exhaust well when applied in cold water due to its polymer chemistry PURONOL 606 is suitable for a wide range of articles. PURONOL 606 results in flat garment leather. PURONOL 606 reduces the fibre tension of the leather fibers and relaxes the wrinkle free appearance.
Safety	: A non hazard product and can be handled with normal Care. Any contact with eye and or spillage on skin should Be washed thoroughly in running water.
Storage	: 6 Months shelf life when stored in doors in sealed containers. Protects from moisture and exposure to sunlight.

Note : If affected by frost the product should be heated to the temperature of 20 to 25° C and stirred before using.



TECHNICAL DATA SHEET

PURONOL-606

APPLICATION :

Shoe Nappa	: 4-6%	PURONOL 606
	: 2-4%	PURONOL SF
Garment	: 8-10%	PURONOL 606
	: 5-6%	PURONOL SE
	: 2-3%	PURONOL SF
Cow Upholstery	: 7-10%	PURONOL 606
	3-4%	PURONOL SE
	2-3%	PURONOL SFO
Buffalo Upholstery	: 12-15%	PURONOL 606 combined with PURONOL SFO
Lining	: 4 -6%	
Chrome Free	: 4 – 6%	with PURONOL SE